











# Poesia

## Caratteristiche/Features/Caracteristiques/Eigenschaften/Eigenschappen/Características Gres Fine Porcellanato – EN 14411 ISO 13006 Gruppo Bla Annex G

	Regulation	Required standards	Refin values
 <p><b>Dimensioni/Sizes/Dimensions/ Abmessungen/Afmetingen/ Dimensiones</b></p>	UNI EN ISO 10545/2	<ul style="list-style-type: none"> <li>→ Lunghezza e larghezza/Length and width/Longueur et largeur/ Länge und Breite/Lengte en breedte/Longitud y anchura</li> <li>→ Spessore/Thickness/Epaisseur/Stärke/Dikte/Grosor ± 5 % max</li> <li>→ Rettilinearità spigoli/Linearity/Rectitude des arêtes/ Kantengeradheit/Rechtheid kanten/Rectitud de los lados ± 0,5 % max</li> <li>→ Ortogonalità/Wedging/Orthogonalité/Rechtwinkligkeit/ Haaksheid hoeken/Ortogonalidad ± 0,5 % max</li> <li>→ Planarità/Warpage/Planéité/Ebenflächigkeit/Vlakheid/ Planitud ± 0,5 % max</li> </ul>	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
 <p><b>Assorbimento acqua/Water absorption/ Absorption d'eau/Wasseraufnahme/ Waterabsorptie/Absorción de agua</b></p>	UNI EN ISO 10545/3	≤ 0,5 %	0,2 %
 <p><b>Resistenza alla flessione/Flexual Strength/ Résistance à la flexion/Biegezugfestigkeit/ Buigvastheid/Resistencia a la flexión</b></p>	UNI EN ISO 10545/4	≥ 35 N/mm <sup>2</sup>	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
 <p><b>Resistenza all'abrasione profonda/Deep abrasion resistance/Resistance à l'abrasion/Bestimmung des Widerstandes gegen Tiefenverschleiß/ Weerstand tegen afschuren/Resistencia a la abrasión profunda</b></p>	UNI EN ISO 10545/6	≤ 175 mm <sup>3</sup>	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
 <p><b>Resistenza agli sbalzi termici/ Thermal shock resistance/Resistance aux écarts de température/ Temperaturwechselbeständigkeit/ Temperatuurswisselingen/Resistencia al choque térmico</b></p>	UNI EN ISO 10545/9	Nessun campione deve presentare difetti visibili/ No sample must show visible defects/ Aucun échantillon ne doit présenter des défauts visibles/ Kein Exemplar darf sichtbare Schäden aufweisen/ Geen enkel monster mag zichtbare gebreken vertonen/ Ninguna muestra debe presentar defectos visibles	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
 <p><b>Resistenza al gelo/Frost resistance/Résistance au gel/Frostwiderstandigkeit/Vorstbestandheid/ Resistencia a la helada</b></p>	UNI EN ISO 10545/12	Resistenti/Resistant/ Résistants/Widerstandsfähig/ Weerbaarstig/Resistentes	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
 <p><b>Resistenza all'attacco chimico/Chemical resistance/Resistance à l'attaque/Chimique/ Beständigkeit gegen Chemikalien/Chemische bestandheid/Resistencia al ataque químico</b></p>	UNI EN ISO 10545/13		Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
 <p><b>Resistenza alle macchie/Stain resistance/ Insensibilité aux taches/Widerstandsfähigkeit gegen fl eckenbildende/Substanzen/Weerstand tegen vlekken/Resistencia a las manchas</b></p>	UNI EN ISO 10545/14	UGL Metodo di prova disponibile/Tests method available/ Methode d'essai disponible/Verfügbares/Prüfverfahren/ Testmethode beschikbaar/Método de prueba disponible	Conforme/Compliant/ Conforme/Entspricht/ Conform/Conforme
 <p><b>Indicazione di resistenza allo scivolamento/ Assessment of slip resistance/Indication de la résistance au glissement/ Bestimmung der Trittsicherheit/Indicatie voor de slipvastheid/ Indicación de resistencia al deslizamiento</b></p>	DIN51130	R	R9 R10 <b>Anticata</b> R11 <b>OUT2.0</b>
	DIN51097	A+B+C	A+B+C <b>Anticata</b>
 <p><b>Coefficiente di attrito dinamico/Measurement of dynamic friction coefficient/Mesure du coefficient de frottement dynamique/Messung des Dynamischen Reibungskoeffizienten/Meting van de dynamische wrijvingscoefficient/Coefficiente de rozamiento dinámico</b></p>	BCRA	> 0,40	Dry 0,45 - Wet 0,46
	BOT 3000	> 0,42	Dry 0,89 - Wet 0,76 <b>Anticata</b> 0,60 0,74 <b>Anticata</b>